



Ultra-Drain Guard[®] Specifications

Material Specifications		
Properties	ASTM Test	Value
Material: Non-Woven, Polypropylene Geotextile	----	----
Grab Tensile	D 4632	220 lbs.
Elongation	D 4632	50%
Trapezoid Tear	D 4533	95 lbs.
Puncture	D 4833	135 lbs.
Mullen Burst	D 3786	420 psi
Permittivity	D 4491	1.5 sec ⁻¹
A.O.S. (U.S. sieve no.)/ Microns	D 4751	80/180
UV Stability (strength retained %) 500 Hours	D 4355	70 %
Fabric Weight (oz./yd ²)(typical)	D 5261	8 oz/ yd ²
Flow (through material)	D 4491	90 gpm/ft ²
Flow (bypass ports gpm) ¹	----	770 gpm
Flow (bypass ports cfs) ¹	----	1.7 cfs

¹Larger bypass flow rate designs are available.

Unit Specifications					
Model	Oil Capture (Gal)	Sediment Capture (lbs)	Collection Area (dia x depth)	Flow Rate (gpm)	Dimensions
Oil & Sediment ² Part # 9217	.87	40	10" x 18"	500	48"x36"x18"
Oil & Sediment ² Part # 9356	1.55	40	10" x 18"	900	60"x60"x18"
Oil & Sediment Plus ² Part # 9219	1.38	40	10" x 18"	500	48"x36"x18"
Oil & Sediment Plus ² Part # 9358	2.06	40	10" x 18"	900	60"x60"x18"
Trash & Debris Part # 9227	----	40	10" x 18"	500	48"x36"x18"
Ultimate ³ Part # 9376	1.57	40	10" x 18"	500	48"x36"x38"
High Capacity Part # 9393	1.9	300	24" x 24"	1000	60"x60"x24"

²Curb-Insert Style available

³Ultimate Model also eliminates bacteria found in stagnant water and catch basins.

02/03/2012